



GETAHINDUS (M) SDN BHD (49583-A)

H.Q : No. 20 & 22, Jalan Selat Selatan 6, Off Jalan Banting, Landpac Industrial Park,
42000 Port Klang, Selangor Darul Ehsan, Malaysia. Tel: 03-31683333 Fax: 03-31683399
E-mail: info@getahindus.com.my Website: http://www.getahindus.com.my
Factory : Lot 809, Batu 13½, Jalan Muar, 84900 Tangkak, Johor Darul Takzim, Malaysia.
Tel: 06-9791188 Fax: 06-9784617



GIVUL 1717

GIVUL 1717

PB/R3/161216/ GIVUL 1717

GIVUL 1717 is a ready-to-use high modulus pre-vulcanised natural rubber latex preserved with ammonia that is suitable for ultra-thin condom dipping. It gives films of high clarity, light color shade and excellent retention of physical properties after ageing at high temperature.

1. TYPICAL PROPERTIES

Total Solid Content (%)	-	60.5
Alkalinity (%)	-	0.65
MST @ 55% TSC (sec.)	-	900
Coagulum Content (ppm)	-	20
B/F Viscosity, 2/60 at 26±2 °C (cps)	-	80
pH	-	10.50

2. TYPICAL DIPPED FILM PROPERTIES OF **GIVUL 1717**

(FILM THICKNESS 0.15 – 0.18mm TESTED IN ACCORDANCE WITH ASTM TEST METHODS)

UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	18.5
Tensile Strength (MPa)	25.0
Elongation at Break (%)	750

AGED (22hrs at 100°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	14.0
Tensile Strength (MPa)	29.0
Elongation at Break (%)	850

The above information is given in good faith and without liability.

3. **APPLICATION**

GIVUL 1717 is specially developed for the production of ultra-thin condom, which requires high bursting pressure property. Its high physical properties and good ageing values allow condom products made to have relatively higher bursting volume, bursting pressures and more consistent yield.

4. **PACKING**

GIVUL 1717 is packed in non-returnable, internal-lined metal drums of net weight 205kg or delivered in larger bulk quantities using appropriate tanks.

5. **STORAGE**

It is recommended that this product be stored in a sheltered premise, away from direct exposure to sunlight or subjected to temperatures above 35°C, but also not in extremely cold or freezing conditions. Some creaming of the product may occur over a long storage period, and if this has happened, stirring or gentle agitation is required to re-disperse the cream into the bulk of the latex before use.

A properly stored product should have a best used period up to 6 months. Longer storage than this period is however not recommended.

6. **TECHNICAL SERVICE AND INFORMATION**

The GETAHINDUS TECHNICAL TEAM comprises of qualified and experienced personnel. All R & D works are carefully thought of and meticulously planned when developing new products and materials to suit customers' requirements. All technical information and samples for evaluation are readily available. For any enquiry, please contact our Sales & Marketing Department.

7. **HEALTH HAZARD AND SAFETY**

Givul 1717 is an ammoniated latex compound containing vulcanizing ingredients. It should not be ingested or consumed. No adverse physiological reactions have been observed when handling the product correctly and using it in the way suggested.

Avoid direct contact with the skin and eyes. If latex is accidentally splashed onto the eyes, wash with plenty of running water and consult a medical doctor immediately, if symptom of eyes discomfort persists