



GETAHINDUS (M) SDN BHD (49583-A)

H.Q : No. 20 & 22, Jalan Selat Selatan 6, Off Jalan Banting, Landpac Industrial Park,
42000 Port Klang, Selangor Darul Ehsan, Malaysia. Tel: 03-31683333 Fax: 03-31683399
E-mail: info@getahindus.com.my Website: http://www.getahindus.com.my
Factory : Lot 809, Batu 13¹/₂, Jalan Muar, 84900 Tangkak, Johor Darul Takzim, Malaysia.
Tel: 06-9791188 Fax: 06-9784617



Givul 2008

Givul 2008

PB/R4/161216/ *Givul 2008*

Givul 2008 is a special low extractable protein, low ammonia preserved medium modulus pre-vulcanised natural rubber latex. It is particularly suitable for manufacturing catheters, dipped medical products and electrician gloves. It provides very high clarity and medium modulus properties to dipped products. It also gives excellent casting and binding characteristics to other latex products. The vulcanization system used in the production of *Givul 2008* complies with the relevant sections of FDA and BfR XXI regulations and specifications.

1. TYPICAL PROPERTIES

Total Solid Content (%)	-	60.5
Alkalinity (%)	-	0.30
MST @ 55% TSC (sec.)	-	800
Coagulum Content (ppm)	-	20
B/F Viscosity, 2/60 at 26±2 °C (cps)	-	70
pH	-	10.50

2. TYPICAL DIPPED FILM PROPERTIES OF *Givul 2008*

(FILM THICKNESS 0.15 – 0.18mm TESTED IN ACCORDANCE WITH ASTM TEST METHODS)

UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	8.0
Tensile Strength (MPa)	25.0
Elongation at Break (%)	900

AGED (22hrs at 100°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	6.0
Tensile Strength (MPa)	36.0
Elongation at Break (%)	950

The above information is given in good faith and without liability.

3. **APPLICATION**

Givul 2008 is suitable for all categories of dipping especially for medical products, electrician gloves, catheters, casting, binding, etc.

4. **PACKING**

Givul 2008 is packed in non-returnable metal drums of net weight 205kg or delivered in bulk tank.

5. **STORAGE**

It is recommended that this product be stored in a sheltered premise, away from direct exposure to sunlight or subjected to temperatures above 35°C, but also not in extremely cold or freezing conditions. Some creaming of the product may occur over a long storage period, and if this has happened, stirring or gentle agitation is required to re-disperse the cream into the bulk of the latex before use.

A properly stored product should have a best used period up to 6 months. Longer storage than this period is however not recommended.

6. **TECHNICAL SERVICE AND INFORMATION**

The GETAHINDUS TECHNICAL TEAM comprises of qualified and experienced personnel. All R & D works are carefully thought of and meticulously planned when developing new products and materials to suit customers' requirements. All technical information and samples for evaluation are readily available. For any enquiry, please contact our Sales & Marketing Department.

7. **HEALTH HAZARD AND SAFETY**

Givul 2008 is an ammoniated latex compound containing vulcanizing ingredients. It should not be ingested or consumed. No adverse physiological reactions have been observed when handling the product correctly and using it in the way suggested.

Avoid direct contact with the skin and eyes. If latex is accidentally splashed onto the eyes, wash with plenty of running water and consult a medical doctor immediately, if symptom of eyes discomfort persists