



GETAHINDUS (M) SDN BHD (49583-A)

H.Q : No. 20 & 22, Jalan Selat Selatan 6, Off Jalan Banting, Landpac Industrial Park,
42000 Port Klang, Selangor Darul Ehsan, Malaysia. Tel: 03-31683333 Fax: 03-31683399
E-mail: info@getahindus.com.my Website: http://www.getahindus.com.my

Factory : Lot 809, Batu 13^{1/2}, Jalan Muar, 84900 Tangkak, Johor Darul Takzim, Malaysia.
Tel: 06-9791188 Fax: 06-9784617



GIVUL VCT

GIVUL VCT

PB/R8/161216/GIVUL VCT

GIVUL VCT is a specially developed prevulcanized latex with high modulus property intended for catheter application. It is also suitable in dipping application such as gloves, finger cot i.e. chlorinated dipped articles.

1. TYPICAL PROPERTIES

Total Solid Content (%)	-	60.0
Alkalinity (%)	-	0.65
MST @ 55% TSC (sec.)	-	1000
Coagulum Content (ppm)	-	20
B/F Viscosity, 2/60 at 26±2 °C (cps)	-	80
pH	-	10.50

2. TYPICAL DIPPED FILM PROPERTIES OF **GIVUL VCT**

(FILM THICKNESS 0.15 – 0.18mm TESTED IN ACCORDANCE WITH ASTM TEST METHODS)

UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	19.0
Tensile Strength (MPa)	26.0
Elongation at Break (%)	800

AGED (22hrs at 100°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	15.0
Tensile Strength (MPa)	28.0
Elongation at Break (%)	900

3. APPLICATION

GIVUL VCT is suitable for all categories of dipping especially for catheters, gloves, finger cots, casting, etc..

The above information is given in good faith and without liability.

4. PACKING

GIVUL VCT is packed in non-returnable metal drums of net weight 205kg or delivered in bulk tank.

5. STORAGE

It is recommended that this product be stored in a sheltered premise, away from direct exposure to sunlight or subjected to temperatures above 35°C, but also not in extremely cold or freezing conditions. Some creaming of the product may occur over a long storage period, and if this has happened, stirring or gentle agitation is required to re-disperse the cream into the bulk of the latex before use.

A properly stored product should have a best used period up to 6 months. Longer storage than this period is however not recommended.

6. TECHNICAL SERVICE AND INFORMATION

The GETAHINDUS TECHNICAL TEAM comprises of qualified and experienced personnel. All R & D works are carefully thought of and meticulously planned when developing new products and materials to suit customers' requirements. All technical information and samples for evaluation are readily available. For any enquiry, please contact our Sales & Marketing Department.

7. HEALTH HAZARD AND SAFETY

GIVUL VCT is an ammoniated latex compound containing vulcanizing ingredients. It should not be ingested or consumed. No adverse physiological reactions have been observed when handling the product correctly and using it in the way suggested.

Avoid direct contact with the skin and eyes. If latex is accidentally splashed onto the eyes, wash with plenty of running water and consult a medical doctor immediately, if symptom of eyes discomfort persists